



High Density Mailer Film

Our co-extruded **multilayer** high density mailer film provides excellent opacity to protect document, prescription or other sensitive material from view or puncture.

APPLICATIONS

- Fulfillment and mail order
- Confidential materials

ADVANTAGES

- High strength, puncture resistant
- Heat sealable
- The non-gloss finish proves a superior print surface for label addressing and barcodes
- Excellent privacy protection
- USPS Compliant

TECHNICAL SPECIFICATIONS

Press Printing: Yes
 Imprinting: Yes
 Mil Thickness: 2.5
 Configuration: EZ™ Bag

Blown Film Properties	Nominal Value(s)	Units	Test Methods (ASTM)
Stress Yield MD	3100	psi	D-882 (A)
Stress Yield TD	3100	psi	D-882 (A)
Tensile Strength MD	8500	psi	D-822
Tensile Strength TD	6500	psi	D-822
Elongation MD	700	%	D-822 (A)
Elongation TD	850	%	D-822 (A)
Tear Propagation MD	500	gf	D-1938
Tear Propagation TD	600	gf	D-1938
Other Properties			
Dart Impact	400	G	D-882
Seal Initiation Temp.	99/210	°C/°F	---
OTR	139	cc/(100in ² *day)	F-1927